

Product Introduction

Alkali Resistant Chopped Strands made from AR-glass fiber is designed for use in dry mix systems or other premixing processes for subsequent moulding into a GRC component. Light in weight and high in strength, glass fiber reinforced cement composited is suitable for skyscrapers, civil engineering, gardens, decorative materials and rural energy installations. It can be used instead of asbestos, or to reinforce plastic, corrosion resistant filter materials and to make chemical industrial tubes.

Product Description

Alkali Resistant Chopped Strand has excellent properties with alkali resistance, bundle-state, stiffness, and aging-proof. It is designed for ease of incorporation even at high dosage and remains integral during mixing. It is used in the manufacture of standard GRC components such as meter boxes or drainage channels, as well as in architectural applications such as decorative screen walling.

Packaging

The following package is available:

Individual 20kg kraft bags
Pallet dimension: 45" x 45"
Bags per pallet: 40

Storage

Unless otherwise specified, it is recommended to store Alkali Resistant Chopped Strands in a cool, dry area. Temperature should not exceed 35°C (95°F) and the relative humidity should be kept below 75%. Alkali Resistant Chopped Strands must remain in packaging material until just prior to their use. If these conditions are respected, the Alkali Resistant Chopped Strands should not undergo significant changes when stored for extended periods of time.

Stacking

To ensure safety and avoid damage to the product, skids should not be stacked more than two high.

Customer Benefits

- Good fluidity
- Easy incorporation, excellent bundle state
- High integrity during mixing
- Abrasion resistant strands
- High durability and excellent alkali resistant
 - a. Soaked in 100°C saturated Ca(OH)₂ solution for 4 hours, and remained filament strength > 82%, diameter diminution < 0.5% (tested in naked fiber without size and coating)
 - b. Soaked in 100°C, 10% NaOH solution for 1 hour, weight loss < 0.5%.



Product Data

ID Number	Filament Diameter (Microns)	Chop Length (mm)	Linear Density (tex)	% ZrO ₂ Content	%LOI Content	% Moisture Content	Breaking Strength (N/tex)
C8-12K-P9E	13 ± 2	12	76 ± 7	≥ 16.0	1.40 ± 0.60	≤ 0.2	≥ 0.25
C8-18K-P9E	13 ± 2	18	76 ± 7	≥ 16.0	1.40 ± 0.60	≤ 0.2	≥ 0.25
C8-24K-P9E	13 ± 2	24	76 ± 7	≥ 16.0	1.40 ± 0.60	≤ 0.2	≥ 0.25

Disclaimer of Liability

This data is offered solely as a guide in the selection of a reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any liability arising out of its use or performance. The user, by accepting the products described herein, agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this data sheet shall not be construed as representations of warranties or as inducements to infringe any patent or violate any law, safety code or insurance regulation.